

## Ri-Lam PO60 SB

**PRODUCT DESCRIPTION / BENEFITS** Ri-Lam PO60 SB series is a self-adhesive film for digitally printed images lamination. The transparent PO face film, UV stabilised, has an external colour stability up to 3 years. The permanent solvent-based adhesive adheres on films printed with solvent, eco-solvent, latex and UV curable inks. The 62 g/m<sup>2</sup> glassine liner provides a good adhesive smoothness. Product REACH & RoHS compliant.

**TYPICAL USE**

- Short term outdoor & indoor lamination film for advertising on Ri-Jet PO100 media
- Protect printed media from abrasion and retard colour fading
- Provide homogeneous gloss finish
- Can be used as a dry erase film

**CONSTRUCTION**

- **Face film:** 60 µm PO film
- **Adhesive:** permanent clear solvent-based acrylic
- **Release liner:** glassine 62 g/m<sup>2</sup>

**Products:**

Clear Gloss finish: code 12635 - **Ri-Lam PO60 Clear Gloss Perm SB N**

**CONVERTING METHOD** Compatible with solvent, eco-solvent, latex and UV inks. To be laminated with a laminator.

**APPLICATION METHOD / INSTRUCTIONS FOR USE** The printed media to laminate should dry minimum 24h prior to lamination. Laminate without tension on the printed media.

**EXPECTED DURABILITY** The expected vertical outdoor durability in Central Europe (zone 1) is 3 years. This information is based on real file experience and artificial aging according to ISO 4892-2. Note: Exposure to severe temperature and ultra-violet light will cause a quicker deterioration. This applies also to polluted area, high altitude, horizontal applications, and south-facing exposure.

**SHELF LIFE** Shelf life is 2 years, when stored at 23 °C and 50 % relative humidity conditions. Higher temperatures and/or humidity levels will reduce product shelf life.

## Ri-Lam PO60 SB

### PHYSICO-CHEMICAL PROPERTIES / TYPICAL VALUES

Face thickness, without adhesive	60 µm	ISO 534-80
Face thickness, with adhesive	80 µm	ISO 534-80
Tensile strength (machine direction)	> 80 N/cm	ISO 527
Elongation at break (machine direction)	>50%	ISO 527
Dimensional stability (1 week @70 °C on glass)	0.3 mm	FTM 14
Initial adhesion on glass (20 minutes)	12 N/25mm	FTM 1
Adhesion on glass (24 hours)	15 N/25mm	FTM 1
Final adhesion on glass (1 week)	20 N/25mm	FTM 1
Minimum application temperature	+10 °C	
Service temperature	From -40 °C to +90 °C	
glassine	62 g/m <sup>2</sup>	ISO 536

### QUALITY CERTIFICATION



### DISCLAIMER

Information on physico-chemical characteristics and values in this document are based upon tests we believe to be reliable and do not constitute a warranty. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use. All technical data are subject to change. All Fedrigoni products are sold subject to terms and conditions of sale. For more information, contact your Fedrigoni sales representative. In case of any ambiguities or differences between the English and foreign versions of this document, the English version shall be prevailing and leading.